



SILICONE UNIVERSAL

UNIVERSAL SILICONE SEALANT



PRODUCT DESCRIPTION

High quality, universal, permanently elastic, water resistant sealant on an acetic acid base. Can be used indoors and outdoors. UV and all-weather resistant.

FIELD OF APPLICATION

Suitable for sealing joints, seams and cracks in all kinds of applications. Suitable for sealings in sanitary and construction applications, for example in the house, glass construction, display case construction, car, boat and caravan. Also suitable for bonding and sealing clear glass, display cases and display windows. Adheres to almost all materials. Not suitable for bitumen, polyethylene, polypropylene, PTFE and aquariums. Not suitable for polyethylene (PE), polypropylene (PP), PTFE and bitumen.

PROPERTIES

- (Sea)water resistant
- Permanently elastic
- UV and all-weather resistant
- Mould resistant
- Excellent bonding on all surfaces
- Chemical resistant
- Colourfast
- Easy to apply
- Resistant to temperatures between -50°C and +120°C

PREPARATION

Working Conditions: Only apply at temperatures between +5°C and +40°C.

Surface Requirements: The surface should be dry, clean and free of dust and grease. Synthetics should first be roughened and/or pre-treated with BISON Silicone Primer.

Preliminary Surface Treatment: For a good result, cover the joint's edges with masking tape. If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

Tools: Apply cartridge with a Power Pistol. Multi Tool to open the cartridge and tooling the sealant.

APPLICATION

Coverage: Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

Directions for use:

Use sealant gun to handle cartridge. Open the cartridge by cutting off the plastic nipple on the top side at the screw thread with a sharp knife. Screw on the nozzle and chamfer at the desired width.

Ensure a minimum joint width of 6 mm and a maximum of 20 mm. The joint depth depends on the joint width. Keep a joint depth of 6 mm up to a joint width of 12 mm. Beyond that, the joint depth should be half the joint width. Inject the sealant evenly into the joint and tool within 10 minutes with a putty knife, moistened with a soap solution. Remove the applied masking tape immediately after tooling. After approx. 10 minutes, a surface skin will form.

Stains/residue: Immediately remove stains with white spirit. Cured sealant can only be removed mechanically.

Points of attention: Silicone hardens under the influence of humidity. Contact with humidity is therefore absolutely necessary during curing. Always consider a joint of at least 6 mm wide.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



SILICONE UNIVERSAL

UNIVERSAL SILICONE SEALANT

TECHNICAL SPECIFICATIONS

100% modulus:	0.3 MPa
Chemical base:	Silicone elastomer
Chemicals resistance:	Very good
Cure rate:	2 mm/24h
Density approx.:	0.99 g/cm ³
Elasticity:	Very good
Elongation of rupture:	500 %
Filling capacity:	Very good
Flash point:	K3 (>55°C)
Hardness (Shore A):	15
Max. allowed distortion:	12.5 %
Minimum temperature resistance:	-30 °C
Maximum temperature resistance:	150 °C
Mildew resistance:	Very good
Moisture resistance:	Very good
Paintability:	Nil
Skinover time:	15 minutes
UV resistance:	Very good
Viscosity:	Pasty
Water resistance:	Very good
100% modulus:	0.3 MPa
Chemical base:	Silicone elastomer
Chemicals resistance:	Very good
Cure rate:	2 mm/24h
Density approx.:	0,99 g/cm ³
Elasticity:	Very good
Elongation of rupture:	500 %
Filling capacity:	Very good
Flash point:	K3 (>55°C)
Hardness (Shore A):	15
Max. allowed distortion:	12.5 %
Minimum temperature resistance:	-30 °C
Maximum temperature resistance:	150 °C
Mildew resistance:	Very good
Moisture resistance:	Very good
Skinover time:	15 minutes

UV resistance:	Very good
Viscosity:	Pasty

STORAGE CONDITIONS

Store in properly sealed packaging in a dry place at between +5°C and +25°C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.