



EPOXY UNIVERSAL 2C SYRINGE

UNIVERSAL STRONG TWO-COMPONENT ADHESIVE



PRODUCT DESCRIPTION

Universal strong two-component adhesive with 50% bio-based 2C formula for repairing metal, pottery, porcelain, glass, pearls, precious stones and various synthetics. Temperature resistant, water resistant, chemical resistant and paintable.

FIELD OF APPLICATION

Suitable for repairs to metal, ceramics, porcelain, crystal, glass, pearls, precious stones and various synthetics (polyester, bakelite, formica, rigid polystyrene and acrylic glass (Perspex®)).

Not suitable for Polyethylene (PE), polypropylene (PP), PTFE and silicone rubber.

PROPERTIES

- Super-strong (up to 190 kg/cm²)
- Resistant to temperatures between -40 °C and +100 °C
- Filling
- Water resistant
- Chemical resistant
- Paintable
- Odourless

PREPARATION

Working Conditions: Only apply at temperatures between +10 °C and +35 °C. Product cures by mixing the resin and the hardener.

Personal safety: Preferably wear gloves.

Surface Requirements: The surface must be dry, clean and free of dust and grease.

Preliminary Surface Treatment: Degrease parts to be bonded with methylated spirit. Roughen smooth surfaces (sandpaper).

Tools: Mix the components by means of the supplied mixing bowl and spatula.

APPLICATION

Coverage: 1 ml = approx 10 cm² at a film thickness of 1 mm

Directions for use:

Remove the spatula from the side of the double syringe, and the closure cap from the handle. Break the seal of the double syringe.

Snap off the nozzle cap. Squeeze the required amount of adhesive into the mixing bowl. Mix thoroughly, then apply to one side of the area to be bonded; for rough materials, apply to both sides. Join the parts together without pressing. At room temperature, the working time is approx. 45 minutes; functional strength is achieved after approx. 6 hours and final strength after 24 hours. Heat accelerates the curing process.

After use, clean the nozzle tips and seal them from the centre of the cartridge using the cap provided. Resin and hardener must not come into contact with each other unless for usage.

Stains/residue: Remove wet stains immediately with warm water and soap. Cured adhesive residue can only be removed mechanically.

Advice: Some types of synthetics can not be joined such as polyethylene and polypropylene. Use a piece of adhesive tape in order to keep the parts in place while the adhesive is curing.

Points of attention: After use close well (note: always place back the cap in the same way, due to the bonding of the cap to the double syringe). For optimum performance it is important to create a larger amount of adhesive and mix it very well. Curing time depends on the temperature. Use only at temperatures between +10 °C and +35 °C

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



EPOXY UNIVERSAL 2C SYRINGE

UNIVERSAL STRONG TWO-COMPONENT ADHESIVE

TECHNICAL SPECIFICATIONS

Bonding technique:	1-Sided application
Chemical base:	Epoxy resin
Chemicals resistance:	Water, oil, grease, solvents, diluted acids and alkalis
Colour:	Opaque, honey coloured
Consistency:	Liquid
Density approx.:	1,1 g/cm ³
Filling capacity:	Very good
Final bond strength (Alu):	19 N/mm ²
Final bond strength after:	24 hours
Handling time:	6 hours
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	100 °C
Moisture resistance:	Good
Mixture ratio:	1:1
Paintability:	Yes
Potlife:	90 minutes
Solvent free:	Yes
UV resistance:	Very good
Viscosity:	Medium viscosity
Viscosity approx.:	35000 mPa·s
Water resistance:	Good
Water soluble:	No

PACK SIZES

24ml/25g

STORAGE CONDITIONS

Store in tightly closed packaging in a dry, cool and frost-free place.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.