



# SILICONE SEALANT SANITARY

## WATER-RESISTANT SILICONE SEALANT FOR ALL SANITARY SEALINGS



### PRODUCT DESCRIPTION

High-quality, permanently elastic and water resistant silicone sealant on an acetic acid base for sanitary seals. Resistant to mould. Loadable with water after 2 hours.

### FIELD OF APPLICATION

Suitable for sealing joints, seams and cracks in bathrooms, kitchens, toilets and showers. Specifically for sealings in sanitary and ceramic applications, such as joints between wall tiles and bath tubs, shower cubicles, bathroom sinks, kitchen counters, sinks and between tiled walls. Adheres to clear glass, ceramics, glazed tiles, enamel, metal, wood and various synthetics. Does not bond to bitumen, polyethylene, polypropylene and PTFE. For acrylic baths, shower basins and synthetic shower walls use BISON Silicone Sealant for Acrylic Baths.

Not suitable for aquariums, acrylic, bitumen, polyethylene (PE), polypropylene (PP) and PTFE

### PROPERTIES

- Mould resistant
- 2 hr Topspeed quality
- (Sea)water resistant
- Chemical resistant
- Colourfast
- Permanently elastic
- UV and all-weather resistant
- Resistant to temperatures between -50°C and +150°C
- Easy to apply

### PREPARATION

**Working Conditions:** Only apply at temperatures between +5°C and +40°C.

**Surface Requirements:** The surface must be dry, clean and free of dust, rust, paint and grease. Synthetics must first be roughened.

**Preliminary Surface Treatment:** For a good result, cover the joint's edges with masking tape. If necessary, prevent three-sided bonding by filling the joint with a foam backer rod or PE film.

**Tools:** Apply cartridge with a Power Pistol. Multi Tool to open the cartridge and tooling the sealant.

### APPLICATION

**Coverage:** Content suitable for approx. 8 to 15 m (depending on the diameter of the joint).

#### Directions for use:

Use sealant gun to handle cartridge. Open the cartridge by cutting off the plastic nipple on the top side at the screw thread with a sharp knife. Screw on the nozzle and chamfer at the desired width.

Ensure a minimum joint width of 6 mm and a maximum of 20 mm. The joint depth depends on the joint width. Keep a joint depth of 6 mm up to a joint width of 12 mm. Beyond that, the joint depth should be half the joint width. Apply the sealant evenly and smooth it within 10 minutes with a mild soap solution (use BISON Multi Tool). Remove the applied masking tape immediately after tooling. After approx. 15 minutes, a surface skin will form. Cured silicone sealant can only be removed mechanically.

**Stains/residue:** Immediately remove stains with white spirit. Cured sealant can be removed mechanically or with BISON silicone sealant residue remover.

**Points of attention:** Silicone hardens under the influence of humidity. Contact with humidity is therefore absolutely necessary during curing. Always consider a joint of at least 6 mm wide. By applying masking tape along the joints completely smooth seams are achieved, remove the tape immediately after smoothing. The sealant is loadable with water after 2 hours, however, do not touch or load mechanically.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.



# SILICONE SEALANT SANITARY

## WATER-RESISTANT SILICONE SEALANT FOR ALL SANITARY SEALINGS

### TECHNICAL SPECIFICATIONS

100% modulus:	0.3 MPa
Chemical base:	Silicone elastomer
Chemicals resistance:	Very good
Cure rate:	2 mm/24h
Density approx.:	0.97 g/cm <sup>3</sup>
Elasticity:	Very good
Elongation of rupture:	600 %
Filling capacity:	Very good
Flash point:	K3 (>55°C)
Hardness (Shore A):	15
Minimum temperature resistance:	-40 °C
Maximum temperature resistance:	120 °C
Mildew resistance:	Very good
Moisture resistance:	Very good
Paintability:	Nil
Skinover time:	15 minutes
UV resistance:	Very good
Viscosity:	Pasty
Water resistance:	Very good

### STORAGE CONDITIONS

Store in properly sealed packaging in a dry place at between +5°C and +25°C.

Our advice is based on extensive research and practical experience. However, in view of the large variety of materials and the conditions under which our products are applied, we assume no responsibility for the results obtained and/or any damage caused by the use of the product. Nevertheless, our Service Department is always at your disposal for any advice needed.